

Product: Premium Polyester Label




Product Features

- Over laminate shields against abrasion and chemicals.
- 0.8 mil general purpose adhesive permanently bonds to many surfaces.
- Highly readable crisp black graphics on white background; color headers available.

Need Asset Labels to Identify Your Assets?

Description

Camcode's **Premium Polyester** label is designed to clearly mark and identify assets. This label is constructed of a 2.0 mil gloss white polyester face stock, over-laminated with a 1.0 mil clear polyester film, and a 0.8 mil general performance permanent pressure-sensitive adhesive. The adhesive offers high initial tack, and is designed to permanently



bond to high and low surface energy plastics, slightly textured, or contoured surfaces. The label has good resistance to general purpose and household cleaners, mild acids, oil and water. Expected exterior life is up to two years.

Product Specifications

Material 2.0 mil gloss white polyester face stock; over-laminated with a 1.0 mil clear polyester film.

Adhesive 0.8 mil high performance permanent pressure-sensitive adhesive.

Label Copy Several font types are available as well as logos or other design elements.

Symbologies All common symbologies available including code 3 of 9, I2 of 5, 128 and Data matrix.

Colors Black graphics on white background; color options available.

Standard Sizes Four standard sizes: 1.50" x .50" – 1.50" x .75" – 2.00" x .75" – 2.00" x 1.00". See price

list for color options and part numbers. Custom sizes available.

Packaging Shipped in sequential order, in rolls, in boxes. 100% no missing numbers.

Shipment 10 working days from receipt of order and approval of artwork. Expedited shipment is

available for an additional charge.



Premium Polyester Labels Durability Characteristics

Product Data	Value	Test Method
Physical Properties Thickness (mile[microns])		ACTIA D 2002
Thickness (mils[microns])	Film: 2.0 (51) +/- 10% Adhesive: 0.8-0.9 (20-23) +/- 0.1 (3) Liner: 3.1 (79) +/- 10%	ASTM D 3652
Dimensional Stability (%)	0.25% MD 0.25% TD	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at160°F (71°C)
Chemical Resistance		
(non-printed stock)	No important and allocations land	ACT AD 006 / 1/5
Household Cleaners	No image or adhesion loss	ASTM D 896 (modified
Mild Acid	No image or adhesion loss No image or adhesion loss	for numbers of cycles and
Oil Water	No image or adhesion loss No image or adhesion loss	cycle time)
	140 mage of duffesion 1033	
Adhesive Properties	On /in (N1/m) average	ACTA D 002
Ultimate Peel from various surfaces Stainless Steel	Oz/in (N/m) average 64(704)	ASTM D 903 (Modified for 72 hr dwell)
Acrylic	68 (748)	(Modified for 72 fil dwell)
Glass	65 (726)	
Polypropylene	Not recommended	
Expected Shear		ASTM D 3654 Method A
Expected Silear	50 hours	a. 1 hour dwell
		b. 1 square inch surface
		c. 4 pound load
Tack	375 gm/sq. cm.	ASTM D 2979
Expected Exterior Life	Up to Two Years	
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C) on most surfaces	
Storage Stability	Two years when stored at 70°F (21°C) and 50% RH.	

Note: Users must test products in the specific environment anticipated. Camcode does not warrant performance of its materials in any environment.

